

OCT-23-2006 14:11

FROM:Dinsmore & Shohl Dayton

9374496405

RECEIVED 01/004 F-954  
CENTRAL FAX CENTER

**Dinsmore & Shohl LLP**  
ATTORNEYS

OCT 23 2006

**FACSIMILE TRANSMITTAL**  
October 23, 2006

from **SUSAN M. LUNA**

Direct: 937-449-6429 / Fax: 937-223-0724 / [susan.luna@dinslaw.com](mailto:susan.luna@dinslaw.com)

**To:** Examiner Long Pham

**Firm:** MAIL STOP APPEAL-BRIEF PATENTS  
Commissioner for Patents

**Fax Number:** 571-273-8300

**Client Number:** MIO 0024 PA/40509.49

**Pages:** 4  
(including cover)

**Comments:** Application of

Applicants	: Jigish D. Trivedi
Serial No.	: 08/915,658
Filed	: August 21, 1997
Title	: LOW RESISTANCE METAL SILICIDE LOCAL INTERCONNECTS AND METHOD OF MAKING
Docket No.	: MIO 0024 PA
Examiner	: Long Pham
Art Unit	: 2814

If there are any problems in receiving this transmission, please call Evelyn Smart at (937) 449-6400 immediately. Thank you.

**Notice**

*This message is intended only for the use of the individuals or entity to which it is addressed and may contain information that is privileged, confidential, and exempt from disclosure under applicable law. If the reader of this notice is not the intended recipient or the employee or agent responsible for delivering this message to the intended recipient, you are hereby notified that any dissemination, distribution or copying of this communication is strictly prohibited. If you have received this notice in error, please notify us immediately by telephone and return these papers to us at the address below via first class mail.*

Dayton • One Dayton Centre • One South Main Street, Suite 1300 • Dayton, OH 45402-2030 • Phone: (937) 449-6400

RECEIVED  
CENTRAL FAX CENTER

OCT 23 2006

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE  
BEFORE THE BOARD OF PATENT APPEALS AND INTERFERENCES

## Application of

Applicants : Jigish D. Trivedi  
Serial No. : 08/915,658  
Filed : August 21, 1997  
Title : LOW RESISTANCE METAL SILICIDE LOCAL INTERCONNECTS  
AND METHOD OF MAKING  
Docket No. : MIO 0024 PA  
Examiner : Long Pham  
Art Unit : 2814

## MAIL STOP APPEAL-BRIEF PATENTS

Commissioner for Patents  
P.O. Box 1450  
Alexandria, VA 22313-1450

<b>CERTIFICATE OF FACSIMILE TRANSMISSION</b>	
I hereby certify that this correspondence is being facsimile transmitted to the centralized facsimile number (571) 273-8300 at the U.S. Patent and Trademark Office on October 23, 2006.	
<i>Suman M. Juna</i>	
Agent	Reg. No. 38,769

Sir:

**RESPONSE TO NOTIFICATION OF NON-COMPLIANT APPEAL BRIEF****(37 CFR §41.37)**

This paper is being filed in response to the Notification of Non-Compliant Appeal Brief (37 CFR §41.37) mailed October 12, 2006. Pursuant to MPEP §1205.03,

(B) When the Office holds the brief to be defective solely due to appellant's failure to provide a summary of the claimed subject matter as required by 37 CFR 41.37(c)(1)(v), an entire new brief need not, and should not, be filed. Rather, a paper providing a summary of the claimed subject matter as required by 37 CFR 41.37(c)(1)(v) will suffice.

Accordingly, appellants are providing herewith a revised Summary of the Claimed Subject Matter in compliance with the rule.

**Summary of Claimed Subject Matter**

The present invention is directed to a low resistance local interconnect which is formed by providing a metal layer over a semiconductor layer, forming a metal silicide layer over the layer of metal, annealing the layers to form a composite structure, and removing unreacted metal from the metal layer.

Serial No. 08/915,658  
Docket MIO 0024 PA

-2-

*Concise explanation of the Subject Matter Defined in Independent Claim 31 and dependent claims 32-34*

Referring to Figs. 3-7 and the specification at page 12, lines 12-29 and page 13, lines 1-16, a composite structure is shown which is formed from a layer of a first metal silicide 34 which is formed over a metal layer 32 (Fig. 3). A layer of photoresist 36 is formed over the metal silicide layer 34 (Fig. 4) and is patterned and etched to form a structure 34A (Fig. 5) which defines the boundaries of the local interconnect. The patterned structure 34A is then reacted with the underlying metal layer 32 by annealing to form a composite structure 37 (Fig. 6). The resulting composite structure 37 includes the first metal silicide, a second metal silicide (formed by the reaction of silicon from first metal silicide 34 with underlying metal 32), and an intermetallic compound which comprises metal from the first metal silicide 34 and metal from the underlying metal layer 32.

As described in the specification at page 7, lines 8-12, the first and second metal silicides each comprise at least one refractory metal selected from chromium, cobalt, molybdenum, nickel, niobium, palladium, platinum, tantalum, titanium, tungsten, and vanadium. The first metal silicide may comprise titanium silicide and the second metal silicide may comprise tungsten silicide.

*Concise explanation of the Subject Matter Defined in Independent Claim 41 and dependent claims 43 and 48-49*

As described in the specification at page 13, lines 6-17, the intermetallic compound in the composite structure is formed by a reaction between the first metal silicide and the second metal silicide. The titanium tungsten intermetallic compound reduces the resistance of the local interconnect.

*Concise explanation of the Subject Matter Defined in Independent Claim 35 and dependent claims 36 and 42*

As described in the specification at page 11, lines 20-28, the local interconnect comprising the composite structure may be used to connect a first active semiconductor region to a second active semiconductor region on a substrate assembly. For example, as shown in Figs.

Serial No. 08/915,658  
Docket MIO 0024 PA

-3-

3-7, the local interconnect may be used to connect a gate (G) of one MOSFET to the drain (D) or source (S) of another MOSFET. As shown, the first and second active semiconductor regions are separated by an insulating region (field oxide 16). As described at page 7, line 22, the composite structure has a thickness of about 700 Angstroms to about 1800 Angstroms.

*Concise explanation of the Subject Matter Defined in Independent Claim 37 and dependent claims 44-45*

As shown in Fig. 8 and as described in the specification at page 14, lines 20-22, one or more interconnects 37 may also be used to connect various structures in an integrated circuit 40, such as the gates of two or more transistors 14, and respective sources to respective drains.

*Concise explanation of the Subject Matter Defined in Independent Claim 38 and dependent claims 39-40 and 46-47*

As shown in Figs. 9 and 10 and as described in the specification at page 14, lines 22-29 and page 15, lines 1-9, one or more local interconnects 37 comprising the composite structure may be used in a memory array such as a static random access memory (SRAM) or a dynamic random access memory (DRAM). The memory array includes a plurality of memory cells 46 arranged in rows and columns and formed on a substrate having at least one semiconductor layer, with each of the plurality of memory cells comprising at least one field effect transistor 14. The local interconnect connects at least one of a source, drain or gate of the field effect transistor in one of the plurality of memory cells to an active area within one memory cell or to one of a source, drain, or gate of the field effect transistor in another one of the plurality of memory cells.

Respectfully submitted,  
DINSMORE & SHOHL LLP

By Susan M. Luna  
Susan M. Luna  
Registration No. 38,769

One Dayton Centre  
One South Main Street, Suite 1300  
Dayton, Ohio 45402-2023  
Telephone: (937) 223-2050  
Facsimile: (937) 223-0724

50058v1